CLAIMS:

1. A polypropylene resin composition comprising:

100 parts by weight of a polypropylene-based composition (D) comprising 50% to 95% by weight of a polypropylene (A), 0% to 25% by weight of an ethylene-α-olefin copolymer rubber and/or aromatic vinyl-containing rubber (B), and 5% to 25% by weight of talc (C) having an average particle diameter of not more than 3μm; and

0.5 to 8.0 parts by weight of a pigment master batch (E) having a hydrogen ion concentration of 5 to 7 and satisfying the expression $0.35 \leqq \eta pig/\eta comp \leqq 1.20$, wherein the ηpig represents a viscosity (poise) of the pigment master batch, and the $\eta comp$ represents a viscosity (poise) of the polypropylene composition (D).

2. The polypropylene resin composition according to claim 1, wherein the talc (C) has a hydrogen ion concentration of 8 to 10.

3. The polypropylene resin composition according to claim 1, which further comprises 0.1 to 2.0 parts by weight of a maleic acid-modified polypropylene (F) having a maleic acid content of 0.1% to 2.0% by weight, a melt flow rate of not less than 30 g/min., and a hydrogen ion concentration of 5 to 6.6.

4. The polypropylene resin composition according to claim 1, wherein the hydrogen ion concentration of the pigment master batch (E) is 5.5 to 6.5, and the pigment master batch (E) satisfies the expression $0.45 \leqq \eta pig/\eta comp \leqq 1.10$.

5. An injection-molded article comprising the polypropylene resin composition of claim 1.